




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B65H 49/08, C09K 3/10, F16L 15/04	A1	(11) International Publication Number: WO 98/47805 (43) International Publication Date: 29 October 1998 (29.10.98)
(21) International Application Number: PCT/IE98/00029 (22) International Filing Date: 17 April 1998 (17.04.98) (30) Priority Data: 970291 18 April 1997 (18.04.97) IE (71) Applicant (for all designated States except US): LOCTITE (R & D) LIMITED [IE/IE]; Tallaght Business Park, Whitestown, Tallaght, Dublin 24 (IE). (72) Inventors; and (75) Inventors/Applicants (for US only): CASEY, Tadhg, Eisirt [IE/IE]; Brookwood, Tubber, Lucan, County Dublin (IE). MARTIN, Francis, Richard [US/IE]; 69 Templeogue Wood, Templeogue, Dublin 6W (IE). CULLEN, Ellen, Patricia [IE/IE]; 31 Dal Riada, Portmarnock, County Dublin (IE). REGAN, Philip, Malcolm [GB/IE]; 16 Oldtown Close, Fallons Road, Naas, County Kildare (IE). (74) Agents: PARKES, Andrew, John, Aykroyd et al.; Tomkins & Co., 5 Dartmouth Road, Dublin 6 (IE).		(81) Designated States: AL, AT, AT (Utility model), CA, CH, CN, DE, DE (Utility model), DK, DK (Utility model), ES, FI, FI (Utility model), GB, JP, KR, LT, LU, LV, MK, MX, PT, RO, RU, SE, SI, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: MATERIAL FOR SEALING THREADED PIPE JOINTS, AND DISPENSER THEREFOR**(57) Abstract**

An article of manufacture which comprises a material for sealing threaded pipe joints comprising a multifilament yarn (7) ready-coated with a joint sealing composition and packaged in a dispenser (1) from which the coated yarn may be supplied for direct application to a threaded area of a pipe. The dispenser comprises a hollow body (1), a cap portion (13) having a dispensing aperture (16) therein and closure means (14) for closing over the aperture when the dispenser is not in use and a multifilament yarn (7) ready-coated with a pipe-joint sealing composition is contained in the body. Suitably, the sealing composition is a non-curing paste composition which comprises an oil and filler, optionally with other ingredients, the oil being selected from linseed oil, silicone oils and mineral oils. Suitably, the yarn is of polyamide or polypropylene.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

5

10

Title of the Invention

15

MATERIAL FOR SEALING THREADED PIPE JOINTS, AND DISPENSER THEREFORField of the Invention

20

This invention relates to material for sealing threaded pipe joints, particularly for use in the plumbing industry for making joints in pipes for water-supply, water-discharge, heating and the like, but also having utility for other types of pipework e.g. in industrial plants. The invention also relates to a dispenser for the material.

25

Brief Description of the Related Art

It is well known for plumbers to use a two-part system of hemp fibre and paste for sealing threaded pipe fittings. Dry hemp fibre is usually supplied in loose unwoven form, and a quantity is taken and drawn out into a length. Hemp is also available in the form of a hank wound on a spool which can be held in a dispenser with a tubular dispensing guide for the hemp. In either case, a length of hemp is wrapped around the threaded area of a male pipe fitting. The paste may be applied to the fitting first, in which case the hemp is drawn through the paste as it is wrapped around the fitting, or alternatively (or in addition) the paste is applied over the hemp. The paste keeps

the hemp in place on the male threaded fitting. The female threaded fitting is then applied and completes the joint. The joint can be adjusted later, if desired.

5

While this two-part system is widely used, it is not acceptable for pipes intended to carry drinking water because hemp does not meet the standards for materials in contact with potable water. Hemp is capable of supporting microbiological growth.

10

An alternative two-part system is available using polypropylene fibre instead of hemp, which system is approved for contact with potable water. However any two-part system has disadvantages because it is cumbersome to use and requires a high degree of skill and takes time to apply.

15

Another commercially available sealing material is a polytetrafluorethylene (PTFE) tape which is non-fibrous in nature. It is typically about 10mm wide and 0.25 - 0.5mm thick. In use, the tape is wound around the threaded area of a male fitting, with a number of overlaps used to build up a thickness as desired. The female threaded part is then applied to complete the assembly. This system also requires skill in application and it suffers the disadvantage that it cannot be used in a joint where readjustment may be necessary without loss in seal.

20

25

Georg Fischer Rohrverbindungstechnik GmbH of D-78224 Singen, Germany, offers for sale a range of The cap materials including pastes for use with hemp and also including a product called PARALIQ PM 35 VLIES which comprises a tape in the form of a synthetic special web, fleece or gauze saturated with a thread sealing paste. It is fibrous in nature like hemp and can be used without either hemp or a separate paste. The tape is 16mm wide and is available in a roll of tape 10m or 25m long. The 25m tape is said to be sufficient for 100 1 inch (25mm) threads (i.e. threads on pipe of 1 inch (25mm) outside diameter). The broad tape is less convenient for the plumber to handle than fibrous hemp or a yarn. It is applied across a number of threads in a band

30

35

- 3 -

16mm wide rather than being wound into individual threads. It is supplied on a roll but not in a dispenser which can be handled by the plumber in one hand.

5

In a different technical field, dental floss is available in the form of a multifilament yarn, optionally waxed, which is wound on a spool and held in a dispenser with a dispensing aperture. A blade for cutting the yarn is located on the exterior of the dispenser, adjacent to the dispensing aperture, for cutting the yarn into desired lengths. Dental floss is not (1) a sealing material or (2) coated with a composition suitable for sealing pipe joints. Accordingly, dental floss does not provide teaching relevant to the field of threaded pipe joints.

15

Summary of the Invention

The present invention provides, as an article of manufacture, a material for sealing threaded pipe joints comprising a multifilament yarn ready-coated with a joint sealing composition and packaged in a dispenser from which the coated yarn may be supplied for direct application to a screw-threaded area of a pipe.

The material according to the invention is more convenient to use than prior art systems. The yarn is easy to wind on to the threaded area of a pipe and it enters into the well of the screw-thread. The material can be handled by a plumber in one hand.

The term "yarn" as used in this description and the following claims includes a "thread".

The dispenser may suitably be hermetically sealed prior to its initial use e.g. by use of a hermetic envelope around it. Desirably also the dispenser has an aperture for dispensing the coated yarn and closure means for closing over the aperture when the dispenser is not in use; such closure means should re-seal the dispenser in a sufficiently airtight manner to allow a shelf life of at least one

week, preferably at least one month, after initial opening of the package, without substantial deterioration of the sealing composition.

5 In one aspect of the invention, the sealing composition may suitably be a non-curing paste composition, for example of the type known for use with hemp in a two-part system for pipe sealing, or an oleoresinous caulk or putty similar to a glazing putty. Such compositions are packaged in sealed conditions to prevent contamination
10 and to minimize exposure to air which could cause deterioration of the composition, for example by drying out (volatilization) or oxidation. The packaging should desirably be air-impermeable and suitably may be such that the sealing composition coated onto the yarn has a shelf life of more than 2 years without significant loss of quality.

15 Suitable non-curing paste compositions comprise a mixture of oil and particulate filler. The oil may suitably be an unsaturated oil (e.g. linseed oil). The particulate filler may suitably be selected from one or more of mineral fillers (e.g. calcium carbonate), powdered
20 polymer fillers (e.g. polyethylene powder or polytetrafluoroethylene powder) and chopped fibre fillers (e.g. chopped aramid fibres, polyethylene fibres or carbon fibres, particularly aramid fibre pulp as described in U.S. Patent 5,068,265 assigned to Loctite, the contents of which are incorporated herein by reference). Mixtures of two or more
25 types of filler may be used. The filler gives the oil body to form the paste. Increased amounts of filler are used to increase the viscosity of the composition. Typical compositions comprise oil and filler in proportions of 20-40 parts by weight oil and 80-60 parts by weight filler. The composition may also contain other resins or plasticizers
30 to aid the composition to adhere to the yarn.

However a joint sealing composition based on linseed oil has some disadvantages including limited shelf stability due to the tendency of
35 linseed oil to oxidize. This results in drying-out of the composition. As already described, sealed packaging can be used to minimize this problem, but special packaging increases the cost of the

- 5 -

final product. Also the composition may dry out too quickly after the package has been opened for use. In addition, linseed oil has been found to leave a residual taste in potable water as result of leaching
5 of oil from the joint sealing composition.

It is desirable therefore in some circumstances to use a non-curing oil other than linseed oil. Silicone oils and minerals oils are two groups of suitable non-curing oils. Silicone oils may in
10 particular be liquid polydimethyl siloxanes such as are listed under CAS Registry Number 63148-62-9. They may suitably have a viscosity in the range from 1,000 mPas to 100,000 mPas and a molecular weight in the range from 10,000 to 500,000. Examples of suitable silicone oils include hydroxyl-terminated polydimethyl siloxane such as Silopren E2
15 from Bayer A.G. or methyl-terminated polydimethyl siloxane such as Silopren W1000, also from Bayer A.G..

Mineral oils may also be used instead of linseed oil. Mineral oils are generally high molecular weight liquid hydrocarbons and are
20 listed under CAS Registry Number 8012-95-1. A suitable example is liquid paraffin. Other suitable examples include Risella oil and Ondina oil from Shell Chemical Company.

The non-curing paste composition desirably has a viscosity in the
25 range from 20,000 mPas to 500,000 mPas, particularly from 50,000 mPas to 100,000 mPas

The advantages of a non-curing composition are (i) that it can be made up without any reactive chemicals and therefore will have minimal
30 toxic effect so that it is suitable for use in systems where food contact approval is necessary, and (ii) that the sealed pipe joint remains adjustable after application of the sealing material without risk of breaking the seal. Furthermore a non-curing composition based on a silicone oil or a mineral oil may have a satisfactory shelf life
35 without being hermetically sealed.

In an alternative aspect of the invention, the sealing

composition may be a curable polymeric composition, more particularly an anaerobic composition, for example an anaerobic thread sealing composition of known type (see U.S. Patents 4,180,640 and 4,243,578 assigned to Loctite). Such a composition may suitably comprise one or more reactive monomers (especially poly- and mono-functional acrylate and methacrylate esters), fillers, stabilizers and curative ingredients. The advantage with a curable composition is that the mechanical strength of the pipe joint can be varied by varying the ingredients of the composition, depending upon the particular application needs and end use of the pipe. In general a material utilizing a curable sealing composition is not primarily intended for use by plumbers but is suitable for sealing joints in other types of pipework e.g. industrial plants.

In the case of a curable sealing composition, the coated yarn will desirably be packaged in a dispenser or other container or packaging which minimizes curing of the composition before use. In the case of an anaerobic sealing composition, the composition will desirably remain in contact with air or oxygen prior to use.

According to one aspect of the invention, a dispenser of material for sealing threaded pipe joints comprises a hollow body, a cap portion having a dispensing aperture therein and closure means for closing over the aperture when the dispenser is not in use, wherein a multifilament yarn ready-coated with a pipe-joint sealing composition is contained in the body.

The multifilament yarn is in generally cylindrical elongate form e.g. as a single strand, which distinguishes it from a web or fleece or gauze. The yarn is suitably of natural fibrous material or of a synthetic polymer, preferably polyamide (e.g. nylon) or polypropylene. Multifilament yarns as used in dental floss may be suitable (see e.g. US Patent 5 560 377 Donovan, the contents of which are incorporated herein by reference), provided that the yarn has the ability to take up the sealing composition. Suitable yarn should be sufficiently soft and pliable to wind around the threaded part of the pipe and sufficiently

absorbent to take up the sealing composition and yet sufficiently strong to tolerate the winding action around the threads on the male component and the screwing-on of the female threaded component, which
5 can cut into and shred an unsuitable yarn. One of the primary functions of the yarn is to act as a jammer in the pipe joint and to give mechanical strength to the threaded assembly. The yarn may also have a property of absorbing water, which can result in some swelling of the material in the joint and effect a better seal. If the sealing
10 material is to be used in contact with food, particularly potable water, then the yarn will desirably be of non-toxic fibre.

The yarn may suitably be spun or may comprise inter-woven and/or entangled filaments or threads. It is preferably in a form comparable
15 to string or twine. It may be in the "dtex" range of 500 to 5,000 (i.e. 500gm to 5,000gm weight per 10,000 metres of yarn), more particularly in the "dtex" range of 900 to 2,500. The decitex or "dtex" is the metric unit for fibre diameter, being the weight in grams of 10,000m of filament (Encyclopedia of Polymer Science and
20 Engineering, 2nd Edition, Vol. 10, p.209). With a heavier material e.g. 2,100 dtex a smaller number of windings on the pipe thread are required to effect a seal as compared to a lighter material e.g. 970 dtex.

25 The uncoated yarn is ordinarily supplied on a spool and the yarn is then coated by conventional methods to an acceptable loading with the sealing composition. An acceptable loading is one which provides an amount of sealing composition on the yarn effective to seal a threaded pipe joint. The loading may suitably be in the range 30-70%
30 w/w (more particularly 40-65% w/w sealing composition on 70-30% w/w (more particularly 60-35% w/w yarn. The yarn may have an external coating of the sealing composition or it may be impregnated or saturated with the composition. This coated yarn is usually then wound back onto smaller spools for use by the plumber or other end user.
35 Each small spool desirably is housed in a sealed dispenser or is stored in sealed packaging for transfer into a dispenser when required for use.

For short-term use, for example for trials, the yarn coated with a linseed-oil based composition may be wound on a roll with a cylindrical cover which encloses the coated yarn on the roll but does not necessarily provide an air-tight seal. This roll and cover may itself be sealed in an air-tight package until it is required for use.

In another alternative aspect of the invention, the coated yarn is not wound on a spool or roll but is wound inside the housing of a dispenser.

Brief Description of the Drawings

Two embodiments of dispensers for use in the present invention will now be described with reference to the accompanying drawings, in which:

Figure 1 is a perspective view of a first embodiment of a dispenser in the closed position.

Figure 2 is a similar view of the dispenser in the open (dispensing) position.

Figure 3 is a detail view of a cap portion of the dispenser.

Figure 4 is a view of a spool of coated yarn for use inside a dispenser of Figure 1 or 2.

Figure 5 is a perspective view of a second embodiment of a dispenser in the closed position.

Figure 6 is a similar view of the second embodiment in an open (dispensing) position.

Figure 7 is a detail view of a cap portion of the second embodiment.

Figure 8 is a view similar to Figure 6 showing the body of the dispenser without the cap portion and partially cut away to show the yarn inside it.

Detailed Description of the Invention

As shown in Figures 1 and 2 the dispenser of the first embodiment

- 9 -

comprises a body 1, suitably of plastics material, which is shaped to receive a spool 2 of coated yarn as shown in Figure 4.

5 The dispenser has a cap portion 3 which fits tightly into the mouth at the top of the body 1 and a lid 4 which can be pivoted from a closed position as shown in Figure 1 to the open position as shown in Figure 2.

10 The cap portion 3 has a slot 5 in the edge which in combination with the body 1 defines a dispensing aperture 6 for withdrawing the coated yarn 7 from the spool 2. There is a cutting blade 8 secured by a rivet 9 on the top surface of the cap portion 3 for cutting the yarn when sufficient yarn has been withdrawn, in a manner similar to dental
15 floss.

 The cap portion 3 has a rib 10 around its skirt which seals against the top edge of the body 1. The lid 4 can be closed down around the cap portion 3 and forms a seal against the body 1 so that
20 the dispensing aperture 6 can be closed over when it is not in use.

 The spool has a base 11 which rests at the bottom of the interior of the body 1 and a spindle 12 which extends upwardly inside body 1 as far as the cap portion 3. The coated yarn 7 is spirally wound onto the
25 spindle 12 so that it may be withdrawn as required.

 Each spool may be disposable after use. The cap portion 3 can be lifted from the body 1 so that an empty spool may be removed and a refill spool can be installed after which the cap portion 3 is pushed
30 back onto the body again. Thus the dispenser can be re-used many times.

 A plumber or other user can hold the body in one hand and pull the coated yarn from the aperture 6 to the desired length, after which the yarn is cut on the blade 8. These simple and quick operations
35 facilitate easy handling of the dispenser and direct application of the coated yarn to the threaded pipe component.

Figures 5 to 8 show a second embodiment of a dispenser. Similar numerals are used for similar parts.

5 In the second embodiment the body 1 and the lid 4 are cylindrical. The lid 4 is not hinged to the body but forms a separate component which has an internal screw thread to mate with an external screw thread 21 on the body 1. The cap portion 13 is also cylindrical and fits tightly into the mouth at the top of the body 1. The cap
10 portion 13 has a dispensing aperture 16 which passes through it. A cutting blade 18, similar to that of a dental floss dispenser, projecting above the cap portion 13 and inclined thereto, is used for cutting the coated yarn 7.

15 As seen in Figure 8, the dispenser does not use a spindle like that of Figure 4. Instead the coated yarn is wound inside the body 1 using a winding technique such as is used in making a ball of string. The yarn can be unwound from an axial passage 22 formed when the yarn is deposited into the body.

20 The first embodiment of Figures 1 to 3 may also be used without a spindle 12 but with the yarn wound inside the body in the manner of Figure 8.

25 Several embodiments of a material according to the invention will now be described by way of example. Viscosity measurements in Examples 3 to 7 were made with a Haake PK100 viscometer, cone PK1,2 degree, after 3 minutes at 20 revs. per second at 25°C.

30 The method for testing pipe joint sealing materials is described in European Standard EN 751-2 : 1996 (British Standard BS EN 751-2 : 1997) "Sealing materials for metallic threaded joints in contact with 1st, 2nd and 3rd family gases and hot water".

35

- 11 -

Example 1

5 A sealant composition was prepared as a paste using the following materials:

	<u>% w/w</u>
Linseed Oil	60
Polyethylene Powder	6
10 Calcium Carbonate	34

Nylon thread of 2100 dtex was coated with this paste composition.

15 100 meters of the nylon thread was coated by passing it through the paste composition twice to give a coating of:

Paste	24 grms
Nylon Thread (100 meters)	21 grms

20 The proportions were therefore:

Paste	53.2% w/w
Nylon Thread	46.8% w/w

25 The coated thread was next wound onto a dispensing spool, for subsequent application to threaded pipe fittings.

30 An experimental assembly was created consisting of a number of screw-threaded couplings of iron pipe fittings of 1 inch (25mm) outside diameter and of 1/2 inch (12.5mm) outside diameter. The threadings of the couplings were of a taper-parallel nature as is typically used by the plumbing industry. One coupling had to be a 1 to 1/2 inch (25mm to 12.5mm) reducer. The assembly when complete had a total seal on one end and a connection capable of attaching a pressure line to the other
35 end. The number of threaded connections on the assembly was four. This assembly when pressurized without the sealing material of the invention in the joints leaked when subjected to very low air

- 12 -

pressure. However when the coated thread of the invention was drawn from the dispenser and applied directly to the screw threads of the couplings (i.e. to the male components) by winding on a sufficient quantity to fill the troughs of about 3-5 screw threads of each coupling, and the female couplings connected on to complete the assembly, and the assembly was pressurized to 6 bar air pressure, no leakage occurred.

10 This demonstrated the satisfactory function of the thread sealant of the invention. The spool of coated thread is packed in an appropriate air-impermeable package prior to use.

Example 2

15 A sealant composition was prepared as a paste using the following materials:

	<u>% w/w</u>
20 Linseed oil	36
Polyethylene powder	5
Calcium carbonate	59.

25 The composition had a viscosity of 35,000 mPas when measured with a Brookfield RVT viscometer, spindle 5, 2.5 revs. per minute at 25°C.

The composition was applied to nylon thread of 2100 dtex as in Example 1. The coated thread was wound into the body of a dispenser.
30 It was subsequently tested as described in Example 1.

35

Example 3

A sealant composition was prepared as a paste using the following
5 materials:

	<u>% w/w</u>
Silicone oil*	32.1
10 Calcium carbonate	67.9

*Silopren E2 from Bayer A.G.

The composition had a viscosity of 28,000 mPas.
15

Nylon thread of 2100 dtex was coated by passing it through this
sealant composition to give a coating at a loading of 52% w/w sealing
composition. The coated fibre weighed approximately 0.45g per metre.

20 The coated thread was wound into the body of a dispenser for
subsequent application to threaded pipe fittings. It did not require
air-tight packaging.

The coated thread drawn from the dispenser was tested as
25 described in Example 1.

30

35

Example 4

A sealant composition was prepared as a paste using the following
5 materials:

	<u>% w/w</u>
Silicone oil*	32.0
10 Polyethylene powder	6.0
Calcium carbonate	62.0

*Silopren E2 from Bayer A.G.

15 The composition had a viscosity of 29,200 mPas.

The composition was applied to nylon thread of 2100 dtex as in
Example 3 at a loading of 60% w/w sealing composition. The coated
fibre had a weight of approximately 0.53g per metre.

20

The coated thread was wound into the body of a dispenser. It was
subsequently tested as described in Example 1.

The paste composition of this Example was subjected to
25 accelerated ageing for two months at 82°C. No weight loss was
observed in the paste.

The coated thread of this Example was also aged for two months at
82°C, samples of the coated thread being packed in a closed plastic
30 container or in a sealed glass container or being left open. The
various samples were then tested for their sealing capability on
threaded pipe joints. No difference was observed between the various
samples or between the aged samples and unaged material. These test
results indicate that the material based on silicone oil will not need
35 to be stored in hermetically sealed containers or packaging.

Example 5

A sealant composition was prepared as a paste using the following materials:

		% w/w
	Silicone oil*	32.0
10	Polytetrafluoroethylene powder	4.0
	Polyethylene powder	6.0
	Calcium carbonate	58.0

*Silopren E2 from Bayer A.G.

15

The composition had a viscosity of 30,620 mPas.

The composition was applied to nylon thread of 2100 dtex as in Example 3 at a loading of 69% w/w sealing composition. The loaded yarn had a weight of 0.7g per metre.

20

The coated thread was wound into the body of a dispenser. It was subsequently tested as described in Example 1.

25

30

35

- 16 -

Example 6

A sealant composition was prepared as a paste using the following
5 materials:

	<u>% w/w</u>
Silicone oil *	35
10 Polyethylene powder	14
Calcium carbonate	51

*Silopren E2 from Bayer A.G..

15 The composition was applied to nylon thread of 2100 dtex as in
Example 3 at a loading of 63% w/w. The coated fibre had a weight of
0.57g per metre.

The coated thread was wound into the body of a dispenser. It was
20 subsequently tested as described in Example 1.

Example 7

A sealant composition was prepared as a paste using the following
25 materials:

	<u>% w/w</u>
Liquid Paraffin	60
30 Polyethylene powder	6
Calcium carbonate	34

The liquid paraffin was a standard product commercially available
35 from the BDH catalogue. The composition had a viscosity of 20,000 mPas.

The composition was applied as in Example 2 and the coated thread

- 17 -

was wound into the body of a dispenser. It was subsequently tested as described in Example 1.

5

10

15

20

25

30

35

CLAIMS

1. An article of manufacture which comprises a material for sealing threaded pipe joints comprising a multifilament yarn ready-coated with a joint sealing composition and packaged in a dispenser from which the coated yarn may be supplied for direct application to a threaded area of a pipe.
2. A material according to claim 1 wherein the dispenser is hermetically sealed prior to its initial use.
3. A material according to claim 1 or 2 wherein the dispenser has an aperture for dispensing the coated yarn and closure means for closing over the aperture when the dispenser is not in use.
4. A material according to claim 1 wherein the sealing composition is a non-curing paste composition.
5. A material according to claim 4 wherein the composition comprises an oil and filler, optionally with other ingredients, the oil being selected from linseed oil, silicone oils and mineral oils.
6. A material according to claim 4 or 5 wherein the composition comprises oil and filler in proportions of 20-40 parts by weight oil and 80-60 parts by weight filler.
7. A material according to claim 1 wherein the sealing composition is a curable polymeric composition.
8. A material according to claim 1 wherein the yarn is of polyamide or polypropylene.
9. A material according to claim 1 which comprises 30-70% w/w sealing composition on 70-30% w/w yarn.

- 19 -

10. A material according to claim 1 wherein the dispenser comprises a hollow body, a cap portion having a dispensing aperture therein and closure means for closing over the aperture when the dispenser is not
5 in use.

11. A dispenser of material for sealing threaded pipe joints comprising a hollow body, a cap portion having a dispensing aperture therein and closure means for closing over the aperture when the
10 dispenser is not in use, wherein a multifilament yarn ready-coated with a pipe-joint sealing composition is contained in the body.

15

20

25

30

35




FIG. 1




FIG. 2




FIG. 3




FIG. 4

2/2




FIG. 5




FIG. 6




FIG. 8




FIG. 7

INTERNATIONAL SEARCH REPORT

national Application No

PCT/IE 98/00029

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B65H49/08 C09K3/10 F16L15/04

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B65H C09K F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 96 16800 A (AKZO NOBEL NV ;MADEREK EUGENIUSZ (DE)) 6 June 1996 see claims 1,2,4-8,18-21 ---	1,4,5,8
A	US 4 606 134 A (FLICK ROBERT A) 19 August 1986 see the whole document ---	1-3,10,11
A	US 5 560 377 A (DONOVAN MARION) 1 October 1996 cited in the application see the whole document ---	1
A	DE 29 00 446 A (LAESER BERNHARD) 30 August 1979 see the whole document ---	1
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

30 July 1998

Date of mailing of the international search report

06/08/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Puetz, C

INTERNATIONAL SEARCH REPORT

national Application No

PCT/IE 98/00029

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 956 089 A (HENRY CROSSLEY (PACKINGS)) 22 April 1964 see the whole document ----	1
A	FR 1 495 195 A (FACOT) 18 December 1967 see the whole document ----	1,4
A	US 5 398 975 A (SIMMONS PAT) 21 March 1995 see column 1, line 6 - line 12 see column 6, line 46 - line 59 see claims ----	1,7
A	US 5 172 841 A (FRIEDMAN LEONARD) 22 December 1992 see the whole document ----	1,10,11
A	DE 22 38 673 A (KLUEBER LUBRICATION) 21 February 1974 see claims 9,19,21 -----	1,4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IE 98/00029

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9616800 A	06-06-1996	AT 167828 T AU 4259596 A EP 0794863 A	15-07-1998 19-06-1996 17-09-1997
US 4606134 A	19-08-1986	NONE	
US 5560377 A	01-10-1996	NONE	
DE 2900446 A	30-08-1979	CH 625327 A	15-09-1981
GB 956089 A		NONE	
FR 1495195 A	18-12-1967	NONE	
US 5398975 A	21-03-1995	NONE	
US 5172841 A	22-12-1992	NONE	
DE 2238673 A	21-02-1974	NONE	

Form PCT/ISA/210 (patent family annex) (July 1992)